

**TECHNICAL DATA SHEET**

Effective From: 14th Aug. 2020

<b>PRODUCT CODE: EB 340</b>	<b>COMMERCIAL NAME: Epoxy , Insulator</b>
<b>DESCRIPTION: Two-components insulator for exotic woods &amp; MDF.</b>	

<b>PROPERTIES</b>	
<b>Recommended for / Main area of application</b>	Two-components transparent insulator for exotic or tanni woods with deep pores. Suggested for the insulation of woods before the application of polyester above all if the wood is painted with stains.
<b>Application Method</b>	By spray, brush
<b>Shelf life</b>	1 year

<b>APPLICATION PROPERTIES</b>		<b>PHISICAL PROPERTIES</b>	
<b>Coverage Area</b>	<b>100 - 120 sqft/lit/coat</b>	<b>Viscosity</b>	<b>45" +/- 5" DIN 2</b>
<b>Vertical Stability</b>	--	<b>Solid Content</b>	<b>17 +/- 2 %</b>
<b>Hardener</b>	<b>H 140 50%</b>	<b>Specific Weight</b>	<b>0.930 +/- 0.020 Kg/Lt</b>
<b>Thinner</b>	<b>T 1460 50-100%</b>	<b>Glossy</b>	-
<b>Pot Life</b>	-	<b>Ph</b>	-

<b>GENERAL INFORMATION</b>			
<b>Drying at 20°C</b>		<b>Oven Drying</b>	
<b>Dust Free</b>	<b>20 min</b>	<b>Time for Flash Off</b>	-
<b>Touch Free</b>	<b>60 min</b>		
<b>Sanding</b>	<b>3 - 4 h</b>	<b>Time for drying</b>	-
<b>Overcoating</b>	<b>Within 6 hours without sanding.</b>		
<b>Stackable</b>	-	<b>Time for cooling</b>	-

A Jubilant Industries Company

OUR VALUES



**Jubilant Agri & Consumer Products Ltd.**  
C-26, Sector 59,  
Noida-201 301, UP, India  
Tel: +91 120 4362205  
Fax: +91 120 2580033  
www.jacpl.co.in

Corporate Office:  
Plot No.# 15, Knowledge Park - II,  
Greater Noida, Distt. Gautam  
Budh Nagar - 201 306, UP, India  
Tel: +91 120 7186000  
Fax: +91 120 7186040, 7186140

Regd Office:  
Bhartiagram, Gajraula  
Distt. Amroha-244 223,  
UP, India

\*This product is Implored from Verinlegno - Italy



**RECOMMENDED APPLICATION PROCESS**

Apply by spray 100 -120 sqft/lit/coat of EB340 - Epoxy , Insulator , catalysed at 100% with H140 and thinned at 50% with T1460 - thinner for matt and sealer. Within 6 hours without sanding or after 6 hours sanding with sand paper 320, apply two hands of poly ether sealer 40' - 60' from each other coat. After 6-8 hours sand with sand paper 220-400 and apply a hand of top coat.

NOTES	User is responsible to make the application of the product in a place with an adequate air- recycle and on respecting of all hygienic and safety regulations.
STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35°C.

**A Jubilant Industries Company**

OUR VALUES



**Jubilant Agri & Consumer Products Ltd.**  
C-26, Sector 59,  
Noida-201 301, UP, India  
Tel: +91 120 4362205  
Fax: +91 120 2580033  
www.jacpl.co.in

Corporate Office:  
Plot No.# 15, Knowledge Park - II,  
Greater Noida, Dist. Gautam  
Budh Nagar - 201 306, UP, India  
Tel : +91 120 7186000  
Fax : +91 120 7186040, 7186140

Regd Office:  
Bhartiagram, Gajraula  
Distt. Amroha-244 223,  
UP, India

\*This product is Implored from Verinlegno - Italy

